TRANSOL GIX I



| Sr.No. | PROPERTY | TEST METHOD | GUARANTEED DATA | |
|--------|----------------------|--------------------------|-------------------------|-------------------------|
| | A. Function | | Minimum | Maximum |
| 1 | Viscosity at 40 °C | IS 1448 (Part 25) | | 15 mm²/s |
| | Viscosity at – 30 °C | IS 1448 (Part 25) | | 1800 mm ² /s |
| 2 | Pour Point | IS 1448 (Part 10/ Sec 2) | | - 40 °C |
| 3 | Water Content | IEC 60814 | | 30 mg/kg (Bulk) |
| | | | | 40 mg/kg (Drum) |
| 4 | Breakdown Voltage | IS 6792 | 30 kV (Delivered) | |
| | | | 70 kV (After Treatment) | |
| 5 | Density at 20 °C | IS 1448 (Part 16) | | 0.895 g/ml |
| 6 | DDF at 90 °C | IS 16086 | | 0.005 |
| 7 | Particle Content | IS 13236 | No general requirement | |

| | B. Refining / Stability | | Minimum | Maximum |
|----|-----------------------------------|------------------------|--------------------------------------|-----------------|
| 8 | Appearance | | Clear, free from sediment & suspend | ed matter |
| 9 | Acidity | IEC 62021 - 1 | | 0.01 mg KOH /gm |
| 10 | Interfacial Tension | ASTM D971 | No general requirement | |
| 11 | Total Sulphur Content | ISO 1459 or ASTM D4294 | No general requirement | |
| 12 | Corrosive Sulphur | DIN 51353 | Not corrosive | |
| 13 | Potentially Corrosive Sulphur | IS 16310 | Not corrosive | |
| 14 | DBDS | IS 16497 (Part 1) | Not detectable (< 5 mg/kg) | |
| 15 | Inhibitors of IS 13631/ IEC 60666 | IS 13631 | (I) Inhibited Oil : 0.08 % - 0.40 % | |
| 16 | Metal Passivator Additives | IS 13631 | Not detectable (< 5 mg/kg) or | |
| | according to IS 13631/ IEC 60666 | | as agreed upon with the purchaser | |
| 17 | Other additives | | NIL | |
| 18 | 2 - Furfural & related | IS 15668 | Not detectable (< 0.05 mg/kg) for ea | |
| | compounds content | | individual compound | |

| | C. Performance | | Minimum | Maximum |
|----|-------------------------------|---------------------------|------------------------|--------------|
| 19 | Oxidation Stability at 120 °C | IS 12422 (Method C) | | |
| | | Test duration | | |
| | | (l) Inhibited Oil : 500 h | | |
| a) | Total acidity | 1.9.4 of 12422 | | 1.2 mg KOH/g |
| b) | Sludge | 1.9.4 of 12422 | | 0.8 % |
| c) | DDF at 90 °C | 1.9.4 of 12422 | | 0.500 |
| 20 | Gassing tendency | IEC 60628, method A | No general requirement | |
| 21 | ECT | See 6.14 | No general requirement | |

| | D. Health , Safety and Environment (HSE) | | Minimum | Maximum |
|----|---|-------------------|----------------------------|---------|
| 22 | Flash point | IS 1448 (Part 21) | 135 ℃ | |
| 23 | PCA content | IP 346 | | 3 % |
| 24 | PCB content | IS 16082 | Not detectable (< 2 mg/kg) | |

- TRANSOL GIX I has an excellent Electrical and Oxidation Stability Properties. It is specially manufactured from highly Refined Base Oil. - The Product fully complies with IS 335:2018, TYPE I, Inhibited specification.